

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Please cancel claim 42 and amend claim 39 as follows:

1. (Twice Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone;

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:

steel in the range of from 20 to 50 percent by weight; and

filler in the range of from 50 to 80 percent by weight,

the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 16 to 40 mesh and between about 80 and 200 mesh, and tungsten carbide particles selected from the group consisting of spherical cemented, crushed cemented, crushed cast, crushed macrocrystalline, and carburized.

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

2. (Original) The rock bit of claim 1 comprising filler in the range of from 60 to 75 percent by weight.
3. (Original) The rock bit of claim 1 wherein the filler comprises in the range of from 20 to 50 percent by weight spherical cast tungsten carbide particles.
4. (Twice Amended) The rock bit of claim 1 wherein the filler comprises in the range of from 40 to ~~[[99]]~~100 percent by weight spherical cast tungsten carbide particles.
5. (Canceled)
6. (Canceled)
7. (Twice Amended) The rock bit of claim ~~[[6]]~~1 wherein the filler comprises spherical cast tungsten carbide particles having ~~[[a]]~~ particle ~~[[size]]~~sizes between about 100 to 200 mesh.
8. (Twice Amended) The rock bit of claim ~~[[5]]~~1 wherein the filler further comprises macrocrystalline tungsten carbide particles having ~~[[a]]~~ particle ~~[[size]]~~sizes between about 40 to 80 mesh.
9. (Amended) A rock bit as recited in claim 1 wherein the hardfacing comprises in the range of from 10 to 90 percent by weight spherical cast tungsten carbide particles having ~~[[a]]~~ particle ~~[[size]]~~sizes between about 16 to 40 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 35 percent by weight of the filler material, the particles having ~~[[a]]~~ particle ~~[[size]]~~sizes in the range of from about 1 to 50 microns.
10. (Original) A rock bit as recited in claim 9 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

cast.

11. (Original) A rock bit as recited in claim 9 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

12. (Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone;

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:

steel in the range of from 20 to 50 percent by weight;

filler in the range of from 50 to 80 percent by weight,

the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having particle sizes between about 80 to 200 mesh.

13. (Original) The rock bit of claim 12 comprising filler in the range of from 60 to 75 percent by weight.

14. (Original) The rock bit of claim 12 wherein the filler comprises in the range of from 20 to 50 percent by weight spherical cast tungsten carbide particles.

15. (Original) The rock bit of claim 12 wherein the filler comprises in the range of from 40 to 100 percent by weight spherical cast tungsten carbide particles.

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

16. (Amended) The rock bit of claim 12 wherein the filler comprises spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 100 to 200 mesh.

17. (Amended) The rock bit of claim 12 wherein the filler comprises in the range of from 10 to 99 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 80 to 200 mesh, and further comprises spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 16 to 40 mesh.

18. (Amended) The rock bit of claim 12 wherein the filler comprises in the range of from 10 to 99 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 80 to 200 mesh, and further comprises tungsten carbide particles selected from the group including spherical cemented, crushed cemented, crushed cast and crushed macrocrystalline.

19. (Amended) The rock bit of claim 18 wherein the filler further comprises macrocrystalline tungsten carbide particles having [[a]] particle [[size]] sizes between about 40 to 80 mesh.

20. (Amended) A rock bit as recited in claim 12 wherein the hard-facing comprises in the range of from 10 to 90 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 80 to 200 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 35 percent by weight of the filler material, the particles having a particle size in the range of from about 1 to 50 microns.

21. (Original) A rock bit as recited in claim 20 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical cast.

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

22. (Original) A rock bit as recited in claim 20 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

23. (Amended) A rock bit comprising:
a body;
at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone;
a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:
steel in the range of from 20 to 50 percent by weight;
filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 16 to 40 mesh and between about 80 to 200 mesh.

24. (Amended) A rock bit as recited in claim 23 wherein the hard-facing comprises in the range of from 10 to 90 percent by weight spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 16 and 40 mesh and between about 80 to 200 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 40 percent by weight of the filler material, the particles having [[a]] particle [[size]] sizes in the range of from about 1 to 50 microns.

25. (Original) A rock bit as recited in claim 24 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical cast.

26. (Original) A rock bit as recited in claim 24 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

27. (Amended) The rock bit of claim 23 wherein the filler comprises spherical cast tungsten carbide particles having [[a]] particle [[size]] sizes between about 100 to 200 mesh.

28. (Twice Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,

steel, and

filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having particle sizes between about 16 mesh to less than 40 mesh.

29. (Twice Amended) A rock bit as recited in claim 28 wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide particles.

30. (Canceled)

31. (Twice Amended) A rock bit as recited in claim 28 further comprising spherical tungsten carbide particles having particle sizes between greater than 80 to 200 mesh.

32. (Twice Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,

steel, and

filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having particle sizes between greater than 80 mesh and 200 mesh.

33. (Twice Amended) A rock bit as recited in claim 32 wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide particles.

34. (Canceled)

35. (Twice Amended) A rock bit as recited in claim 32 further comprising spherical tungsten carbide particles having particle sizes between 16 to less than 40 mesh.

36. (Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,

steel, and

filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having particle sizes between about 16 to 40 mesh and between about 80 to 200 mesh.

Appln No. 09/637,764
Amdt date February 7, 2008
Reply to Office action of March 7, 2006

37. (Amended) A rock bit as recited in claim 36 comprising steel in the range of 20 to 50 percent by weight, and wherein the spherical tungsten carbide particles have particle sizes between about 16 to less than 40 mesh and between greater than 80 to 200 mesh.

38. (Canceled).

39. (Thrice Amended) A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,

steel, and

filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 19 to 100 percent by weight spherical cast tungsten carbide particles.

40. (Amended) A rock bit as recited in claim 28 wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide.

41. (Amended) A rock bit as recited in claim 32 wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide.

42. (Canceled).